
FIVE YEAR SPECIFICATION FOR VFI-690 WATERPROOFING PRIMER

1 GENERAL:

1.01 General System Description

- A.** VFI-690 Waterproofing Primer is designed to seal pores and small cracks in all types of masonry walls prior to top coating with an exterior acrylic coating.
- B.** Specifications here include guidelines for preparation, and coating of the masonry surface. This is a general installation guide specification and is not a project-specific specification. It is the responsibility of the owner, project manager and contractor to ensure that this general installation guide is followed when work pertains to the project.
- C.** A Volatile Free, Inc. Technical Representative shall approve in writing any material substitutions, deviations from and/or addendums to this specification.

1.02 Contractor to:

- A.** Provide all labor and materials, equipment and accessories necessary to repair, clean and prepare existing surfaces to receive VFI-690 Waterproofing Primer. Install Volatile Free, Inc.'s coatings in accordance with this specification and manufacturer's instructions. Reference the following sections for more detailed information.
 - 1. Environmental requirements (1.07)
 - 2. Quality Preparation Program (1.08)
 - 3. Preparation of the surface to receive work. (3.01-3.02)
 - 4. Install Acrylic Coating System. (3.03 - 3.05)
 - 5. Warranty (5.0)

1.03 Approved Materials and Contractors:

- A.** The contractor and materials associated with the project shall be used only if approved by VFI and Owner.
- B.** The applicator must have a current Certification certificate from Volatile Free, Inc.
- C.** VFI shall be a single source of the waterproofing system.
- D.** The contractor's qualifications and equipment must be approved by VFI.
- E.** Unspecified materials shall be submitted to the architect/ owner for approval prior to the bid date. In requesting approval, a letter of certification must be signed by an officer of the manufacturer, stating that the alternative material is equal to or better than the specified product. The manufacturer shall have a minimum of five years manufacturing experience.

1.04 Submittals:

A. Manufacture:

1. VFI's published technical data, and SDS on all products to be used on project.
2. Contractor's certification certificate issued prior to bid date from VFI.

1.05 Product Delivery, Storage, and Handling:

- A. Deliver VFI materials in unopened containers with VFI labels affixed. Include the following on the label of each container: Manufacturer's name, product name, product type, lot number, mixing instructions, and precautions.
- B. Contractor shall have materials delivered in sufficient quantities so as not to cause delays in the work.
- C. Contractors shall be responsible for storage and protection of all materials required. Materials shall be stored in a manner so as not to exceed the VFI specified temperature limitations. (see product label or data sheet) In all cases, the storage and handling of materials shall conform to the requirements of VFI and the applicable safety regulatory agencies.
- D. It is the responsibility of the contractor to calculate and add a loss factor due to wind, surface profile and overspray.

1.06 Pre-Construction Conference:

- A. Prior to the start of the project, a meeting shall be held at the job site attended by the Contractor's Representative, Technical representation of VFI, and the Owner's representative to review materials, application procedures, and all items associated to this phase of the work. **(Optional)**

1.07 Environmental Requirements:

- A. Install all materials in strict accordance with all published safety, weather and temperature precautions given by VFI.
- B. The contractor is to take precautions to protect this building project, other adjacent facilities and property.
- C. Do not install coating materials under the following conditions:
 1. When surfaces are wet or rain is imminent
 2. **Spray Application-** When wind velocity is above fifteen (15) MPH without using a windscreen. In conjunction with a wind screen, protective coverings must be fastened to stay secure in wind and be vented if used in conjunction with preventing moisture collection.
 3. Do not install VFI-690 when the temperature is below 50° F.

1.08 Quality Preparation Program:

- A. All products must be mixed with proper equipment on the day of application. See product label or Product Data Sheet for instructions.
- B. Coating thickness shall be checked during application for proper thickness per

FIVE YEAR SPECIFICATION FOR VFI-690 WATERPROOFING PRIMER

SUSTAINABILITY.
DURABILITY.
FLEXIBILITY.

specification; as stated on the warranty procedures or on work order, whichever is greater.

2 PRODUCTS:

2.01 Materials:

- A. All products listed are manufactured, supplied, or approved by VFI of Brookfield, Wisconsin.
 - 1. Wash: VFI-1009 Cleaning Concentrate
 - 2. Rust Primer: VFI-1074
 - 3. Crack Repairs and Sealer for Through-Wall Penetrations: VFI-630 Acrylic Flashing Grade
 - 4. Coating: VFI-690 Waterproofing Primer

This coating, shall meet the following mean technical requirements:

a. Solids:	by Volume	51%
b. Tensile:	ASTM D-2370	350 +/- 50 psi
c. Elongation:	ASTM D-2370	200% +/- 25%
d. Permeance	ASTM D-1653	27(wet), 13(dry)
e. Flexibility @ 0° mandrel (pass/ fail)	ASTM D-522B	Pass
f. Fungi Resistance (pass/ fail)	ASTM G-21	Pass
g. Accelerated Weatherability @ 1,000 Hrs. (pass/ fail)	ASTM D-4798	Pass
h. VFI-630 Flashing Grade Acrylic		

2.02 Other Materials Required:

- A. All other materials shall be approved by VFI as per Section 1.04, A.

3 EXECUTION:

NOTE: Care must be taken to ensure that the substrate is dry and properly prepared. The owner and/or contractor must correct any defect in the condition of the existing substrate prior to the coating, otherwise, these defects may adversely affect the condition of the coating over time, necessitating maintenance and/or repair and affecting the warranty. The contractor is responsible in making sure the existing substrate is sound.

3.01 Surface Preparation:

- A. All surfaces shall be clean and dry, and free of any dirt, dust, oil, surface chemicals or other contaminants which may be detrimental to optimum adhesion of the coating.
- B. The existing surface is to be repaired where necessary.

3.02 Surface Wash:

NOTE: Allow surface to dry before applying VFI-1009 Cleaning Concentrate

- A. VFI-1009 Cleaning Concentrate should be diluted at a 1:10 ratio with water. Apply the diluted cleaning solution to the dry substrate under low pressure using a Hudson type agricultural sprayer **at the rate of 2,000 sq. ft. per gallon of VFI-1009**. Allow the solution to stand for a minimum of 15 minutes. Extremely stubborn areas may require treatment with a more concentrated dilution. Power wash the surface with a minimum 2,000 psi power washer.
- B. Repeat rinsing as required to remove all cleaning solution. Allow the substrate to completely dry prior to the application of any coating materials.
- C. Use concentrated chlorine solution to treat areas of mildew, fungus, or algae.
- D. All cleaning agents must be rinsed off of and allowed to dry before proceeding.

NOTE: It is crucial to ensure that the preexisting substrate is clean and dry prior to coating with the VFI system.

3.03 Repair of Surface Defects:

Seal all cracks, holes, voids, through-wall penetrations, and other defects in the existing substrate using VFI-630 Flashing Grade Acrylic Coating.

One gallon of VFI-630 will treat approximately 150 lineal feet of cracks.

3.04 Coating Application:

Apply 1 coats of VFI-690 by brush, roller, or airless sprayer with backroll, **at a combined coverage rate of 0.8 gallons per 100 sq. ft. (12 wet mils, 6 dry mils).**

3.05 Exterior Acrylic Coating

Apply exterior acrylic coating of the owner's choice following manufacturer's guidelines.

NOTE: VFI recommends adding a loss factor due to wind, surface profile and overspray. It is the responsibility of the contractor to calculate the correct amount of material to achieve the required dry film mils as per specification.

4 FIELD QUALITY CONTROL:

4.01 Inspection:

- A. **Coating Thickness:** The finished dry film thickness will measure a minimum of 6 mils.
- B. **Defects:** There shall be no delamination, lifting blisters, pinholes, voids, or membrane defects of any kind.

- C. Variations:** Any variations from specified procedures or limits found by the contractor, representatives of VFI, or the owner, shall be immediately corrected by the contractor at their own expense.

4.02 Job Site Clean up

- A.** Clean up all debris, excess materials and equipment and remove from site.

5 WARRANTY:

5.01 Requirements:

- A.** VFI warrants that the material supplied will meet or exceed physical properties as published.

**FIVE YEAR SPECIFICATION FOR
VFI-690 WATERPROOFING PRIMER**

**SUSTAINABILITY.
DURABILITY.
FLEXIBILITY.**

WARRANTY SPECIFICATION/AFFIRMATION OF SIGNATURES

Type of Warranty:

- A. Volatile Free, Inc. Five Year Warranty covering material shall be issued within thirty (30) days of final payment and successful roof inspection.

Substrate selected:

Application rate required:

Application method:

Volatile Free Inc.

Printed Name:

Title:

Date Approved:

Warranty Project #

Applicator

Printed Name:

Title: _____

Company: _____

Address: _____

City, State: _____

Telephone: _____

Please sign and date below to acknowledge that you read and understand the FIVE YEAR SPECIFICATION FOR VFI-690.

PLEASE SEND THIS SIGNED COPY TO VOLATILE FREE, INC.; 19500 JANACEK COURT, BROOKFIELD, WI 53045 OR FAX: 262-787-0500

Signature

DATE

FIVE YEAR SPECIFICATION FOR VFI-690 WATERPROOFING PRIMER

SUSTAINABILITY.
DURABILITY.
FLEXIBILITY.

THIS INFORMATION AND TECHNICAL ADVICE PROVIDED HEREIN ARE BELIEVED TO BE RELIABLE AND ACCURATE TO THE BEST KNOWLEDGE OF VOLATILE FREE, INC., AS BASED ON TESTS AND SHOULD SERVE ONLY AS A RECOMMENDATION. AS THE MANUFACTURER, VOLATILE FREE, INC. MAKES NO REPRESENTATIONS OR WARRANTIES OF ANY KIND, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR USE OR A PARTICULAR PURPOSE FOR THE PRODUCT. VOLATILE FREE, INC. MAKES NO REPRESENTATIONS OR WARRANTIES AS TO THE RESULTS OF THE USE OF THE PRODUCT AND ASSUMES NO OBLIGATION OR LIABILITY IN CONNECTION THEREWITH. VOLATILE FREE, INC. IS NOT LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES OF ANY SORT FROM USE OF THIS PRODUCT. THE INFORMATION PROVIDED HEREIN IS SUBJECT TO CHANGE AT ANYTIME WITHOUT NOTICE. INFORMATION CHANGES MAY INCLUDE, BUT ARE NOT LIMITED TO, COMMERCIAL AND TECHNICAL CHANGES, CHANGES IN PRICING, PHYSICAL CHARACTERISTICS AND PACKAGING.

Setting the standard for Renewable Coatings and Spray Foams

Corporate Office: P.O. Box 344 . Brookfield, WI 53008 . (800) 307-9218 . (262) 787-0400 . Fax (262) 787-0500

www.volatilifree.com