



VFI-607 SINGLE COMPONENT ACRYLIC BASECOAT/PRIMER

Overview

Description

VFI-607 is a water-borne, single component, acrylic basecoat/primer characterized by excellent strength, water resistance, asphalt bleed blocking and weatherability.

Usage

Applicable uses include the following:

- Protective primer/basecoating system for exterior asphalt, built up roof, cap sheet or any roofing substrate that may leach hydrocarbon oils/liquids.
- Basecoat/primer for acrylic or silicone topcoats that can be impregnated with reinforcing fabric to add strength to non-reinforced surfaces.

Limitations

- DO NOT** apply to surfaces where substrate or ambient temperatures are below 45°F.
- DO NOT** apply directly to single ply membranes or any other surfaces that are not asphalt based without a primer or prior approval from a Volatile Free, Inc representative.
- DO NOT** apply when there is a possibility of temperatures falling below 32°F within a 4 hour period after application, or rain is in the forecast.

- Color**
Blue

Physical Properties

Hardness

ASTM D-2240
Shore A 70-75

Tensile Properties

ASTM D-412
Strength 600 psi min
Elongation 600%

Tear Resistance

ASTM D-624
Die C 100 pli min

Flammability

Not Rated. If a rated system is needed use VFI-605 and VFI-650. They have passed ASTM E-108 Class A over VFI-727 foam.

Adhesion

Good adhesion to asphaltic substrates, masonry, and concrete. A primer must be used for single ply recoat and on ferrous metals to prevent corrosion. Contact Volatile Free, Inc. for specific recommendations, or further details.

Weather & Environmental Performance

Dry Time

1-2 hours at 72°F, 50% RH

Cool Roof Test Results

Adhesion varies based asphaltic substrate. Adhesion failure is generally due to limitations of asphaltic substrate, not VFI-607 adhesion.

Surface Tack

Residual tack will vary depending on how long the coating is directly exposed to heat prior topcoating.

Liquid Component Properties

- **Coverage**
100-200 sq ft/gallon depending on roughness of substrate or fabric embedding.
- **Solids**
Method 4041, fed. Std. 141
Weight 45.0%
Volume 40.5%
- **VOC**
Contains less than 25 grams/liter
- **Packaging and Shelf Life**
12 months shelf life between 40°F and 72°F. Protect from freezing below 32°F. Available in 1 gallon and 5 gallon pails and 55 gallon drums.
- **Thinning**
Thinning is not recommended under normal conditions. When necessary, VFI-607 can be thinned up to 5% with water. Thinning causes reduction in film build and changes flow properties.

Application

Prior to applying VFI-607, ensure that surfaces to be coated are clean and dry, and free of loose dirt or particles. Make sure to mix, shake or stir VFI-607 prior to use.

Apply by spray, roller or brush. A wide range of spray equipment can be used including airless spray or conventional spray.

Apply VFI-607 at a rate of 100-200 sq/ft gallon to the asphaltic substrate. Coverage will depend on a variety of factors such as granule profile, porosity of substrate, general roughness of substrate.

Allow VFI-607 to dry thoroughly prior to topcoating with VFI-605, VFI-650 or VFI-991. The surface will still contain residual tack, but coating will not transfer to finger with touch.

When using VFI-607 to embed fabric, apply the VFI-607 only to the area to be covered with one sheet of reinforcing fabric at a time. Once the bottom or fabric is anchored and embedded, coat the top of the fabric with VFI-607 at a rate of 2-3 gallons per 100 square feet.

The fabric/VFI-607 will serve as a basecoat to be topped with an acrylic or silicone topcoat.

Clean up with water supplemented with liquid detergent. Spray equipment should be given a final cleansing with MEK thinner or lacquer thinner to remove moisture, and prevent possible corrosion.

VFI-607 products are water based and will require the complete evaporation of water to achieve cure.

For more information, contact us today at **800-307-9218**

Setting the standard for Renewable Coatings and Spray Foams

Corporate Office: P.O. Box 344 • Brookfield, WI 53008 • (800) 307-9218 • (262) 787-0400 • Fax (262) 787-0500 • www.volatilifree.com

This information and technical advice provided herein are believed to be reliable and accurate to the best knowledge of Volatile Free, Inc. As based on tests and should serve only as a recommendation. As the manufacturer, Volatile Free, Inc. makes no representations or warranties of any kind, expressed, implied or statutory, including but not limited to all implied warranties of merchantability or fitness for use or a particular purpose, or any other matter with respect to this product. Volatile Free, Inc. makes no representations or warranties as to the results of the use of the product and assumes no obligation or liability in connection therewith. Volatile Free, Inc. is not liable for any special, exemplary, punitive, incidental or consequential damages of any sort or kind from use of this product. The information provided herein is subject to change at any time without notice. Information changes may include, but are not limited to, commercial and technical changes, changes in pricing, physical characteristics and packaging.